

## A5052BE

化学成分 (%)								
Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0.25以下	0.40以下	0.10以下	0.10以下	2.2~2.8	0.15~0.35	0.10以下	—	残部

母材		調質	直径公差(mm)
直径(mm)	長さ(mm)		
32	2000	H112	± 0.39
35	2000	H112	± 0.46
40	2000	H112	± 0.52
45	2000	H112	± 0.59
50	2000	H112	± 0.72
55	2000	H112	± 0.85
60	2000	H112	± 1.00
65	2000	H112	± 1.30
70	2000	H112	± 1.40
75	2000	H112	± 1.70
80	2000	H112	± 2.10
85	2000	H112	± 2.70
90	2000	H112	—
95	2000	H112	—
100	2000	H112	—
110	2000	H112	—
120	2000	H112	—
130	2000	H112	—
140	2000	H112	—
150	2000	H112	—
160	2000	H112	—
170	2000	H112	—
180	2000	H112	—
190	2000	H112	—
200	2000	H112	—
210	2000	H112	—
220	2000	H112	—
230	2000	H112	—
240	2000	H112	—
250	2000	H112	—
260	2000	H112	—
270	2000	H112	—
280	2000	H112	—
290	2000	H112	—
300	2000	H112	—
310	2000	H112	—
320	2000	H112	—
330	2000	H112	—
350	2000	H112	—
360	2000	H112	—

機械的性質		
引張強さ(N/mm²)	耐力(N/mm²)	延び(%)
175以上	70以上	—