

A6063TE-T5

化学成分 (%)								
Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0.2~0.6	0.35以下	0.10以下	0.10以下	0.45~0.9	0.10以下	0.10以下	0.10以下	残部

押出丸管



寸法 (mm)		
D	t	長さ
10	1.0	4000
10	1.5	4000
10	2.0	4000
11	1.0	4000
12	1.0	4000
12	1.5	4000
12	2.0	4000
13	1.0	4000
13	1.5	4000
14	1.0	4000
14	1.5	4000
14	2.0	4000
15	1.0	4000
15	1.5	4000
15	2.0	4000
16	1.0	4000
16	1.5	4000
16	2.0	4000
18	1.0	4000
18	1.5	4000
18	2.0	4000
19	1.0	4000
19	1.5	4000
19	2.0	4000
20	1.0	4000
20	1.5	4000
20	2.0	4000
20	2.5	4000
20	3.0	4000
22	1.0	4000
22	1.5	4000
22	2.0	4000
22	3.0	4000
25	1.0	4000
25	1.5	4000
25	2.0	4000
25	2.5	4000
25	3.0	4000

押出丸管



寸法 (mm)		
D	t	長さ
28	1.0	4000
28	1.5	4000
28	2.0	4000
28	3.0	4000
30	1.0	4000
30	1.5	4000
30	2.0	4000
30	2.5	4000
30	3.0	4000
30	4.0	4000
32	1.0	4000
32	1.5	4000
32	2.0	4000
32	3.0	4000
35	1.5	4000
35	2.0	4000
35	2.5	4000
35	3.0	4000
35	4.0	4000
38	1.5	4000
38	2.0	4000
38	3.0	4000
40	1.5	4000
40	2.0	4000
40	2.5	4000
40	3.0	4000
40	4.0	4000
40	5.0	4000
42	2.0	4000
45	1.5	4000
45	2.0	4000
45	3.0	4000
45	5.0	4000
50	1.5	4000
50	2.0	4000
50	2.5	4000
50	3.0	4000
50	4.0	4000
50	5.0	4000

押出丸管



寸法 (mm)		
D	t	長さ
55	2.0	4000
55	3.0	4000
60	2.0	4000
60	3.0	4000
60	4.0	4000
60	5.0	4000
65	2.0	4000
65	3.0	4000
70	2.0	4000
70	3.0	4000
70	4.0	4000
70	5.0	4000
75	3.0	4000
80	3.0	4000
80	4.0	4000
80	5.0	4000
90	3.0	4000
90	5.0	4000
100	3.0	4000
100	5.0	4000
110	3.0	4000
110	5.0	4000
120	3.0	4000
120	5.0	4000
130	5.0	4000
140	5.0	4000
150	5.0	4000
160	5.0	4000
180	5.0	4000
200	5.0	4000